

TO THE REAL

Elevated screed Betonwood TG

16. SLABS

Complete dry system for elevated screeds with a single layer of high density BetonWood TG cement bonded particle boards on adjustable supports

Complete dry system for elevated screeds with a single layer of high density BetonWood TG cement bonded particle boards on adjustable supports. Excellent construction system for high performance floating screeds.

STRATIGRAPHY		DESCRIPTION	QUANTITY m ²	PRICE €/m²	AMOUNT
1	Cement bonded particle boards BetonWood tongue&groove	Pressed cement bonded particle boards with high compactness, density and hardness, resistant to fire, to atmospheric agents, with excellent thermal and acoustic insulation characteristics, with tongue&groove edges. The panels are made of Portland-type concrete conglomerate and debarked Pine wood fiber: high density δ =1350 Kg/m ³ , coefficient of thermal conductivity λ =0,26 W/mK, specific heat c=1.88 KJ / Kg K, coefficient of resistance to vapor penetration μ =22,6 and fire reaction class A2-fl-s1, according to EN 13501-1. The dimensions are mm for a thickness of mm. The wood used in panel processing comes from forests controlled by FSC reforestation cycles and pressed with water and hydraulic binder (Portland cement) with high cold compression ratios.			0
2	Adjustable supports	Adjustable Floor Stands have anti-noise rubber head, specific adjustment key, variable heights, pre-cut base for wall corner cutting. Possibility to adjust the height millimetrically (adjustable from 25 to 270 mm), in favor of a perfect leveling of the flooring.			0
3	Foundation	Existing or new building foundation			
		TAX IVA 22%	0	TAXABLE	0
TOTAL AM			TAL AMOUNT	0	



The functionality of the system will be covered by a BetonWood guarantee for the characteristics of air tightness, water proofing and isolation of the technological package. The warranty will be documented with the appropriate Certificate and Certificate of Assurance that will be delivered at the end of the work to the DD.LL. from the same layer. The forms are available on the BetonWood website as well as the technical indications, the application matrix and the exclusion clauses.