


13a. ROOFS

Roof C Bitumfiber - therm and bitumfiber



Ecological roof systems for thermo-acoustic insulation with Therm wood fiber density 160 kg/m³ and Bitumfiber wood fiber density 280 kg/m³ on concrete

Complete dry system for high-displacement thermal roofs with Fibertherm wood fiber insulation panels and high-density Bitumfiber wood fiber panels on concrete structure. Excellent system for thermo-acoustic insulation of roofs.

STRATIGRAPHY	DESCRIPTION	QUANTITY m ²	PRICE €/m ²	AMOUNT
1 Roof tiles	Roof tiles			
2 Support-Spacer type Aercoppo	An element, weighing 36 g, made of polypropylene copolymer stabilized to U.V.A. rays, with the function of raising and anchoring, to be applied on the back of each tile roof. It creates, a true ventilation chamber of 600 cm ² /m underlay, raising the channel tile only 3.5 cm from the laying surface.			0
3 Anti-steam barrier FiberTherm multi UDB	High airtight sealant vapor barrier for renovation solutions. Extreme ease of installation for safe and simple use. It has an integrated adhesive strip to secure joints and can be used as a temporary cover. Size: 1,50 m x 50 m Roll surface: 75m ² Weight approx.160 g/m ²			0
4 Bituminous wood fiber Bitumfiber thickness 23 mm	BitumFiber bituminous wood fiber panel is the optimal combination for high strength in dry and wet screed construction. The material is characterized by the following thermodynamic characteristics: density approx. 280 (+20-10) kg/m ³ , coefficient of thermal conductivity λ=0,050 W/mK, coefficient of resistance to vapor penetration μ=5, specific heat c=2100 J/Kg K and reaction to fire class E, according to EN 13501-1 standard, CE certified. The wood used in the processing of the panels comes from forests controlled by FSC reforestation cycles.			0
5 Wood fiber panels Fibertherm 160 (2 layers) available thicknesses: 60+60 mm 80+80 mm 100+100 mm	The panels are made of wood fiber with density δ=160 Kg/m ³ , are produced with a wet system, in compliance with EN 13171 and EN 13986 standards under constant quality control. The material is characterized by the following thermodynamic characteristics: coefficient of thermal conductivity λ=0.039 W/mK, specific heat c=2100 J/Kg K, coefficient of resistance to vapor penetration μ=5 and reaction to fire class E, according to EN 13501-1 standard. The dimensions of the panels correspond to ... mm for a thickness of ... mm. The wood used in the processing of the panels comes from forests controlled by FSC reforestation cycles.			0
6 Steam brake FiberTherm multi membra 5	Steam brake for better airtightness on the outer side of the roof, resistant to UV rays, excellent adhesion properties and tear resistance. Size: 1,50 mx50 m Roll surface: 75m ² Weight approx.110 g/m ²			0
7 Concrete roof	Concrete structure with slats and hollow bricks thickness 200+40 mm			
TAX IVA 22%		0	TAXABLE	0
TOTAL AMOUNT				0