

## 13. ROOFS



## Roof C Isorel - therm and isorel

Ecological roof systems for thermo-acoustic insulation with Therm wood fiber density  $160 \text{ kg/m}^3$  and Isorel wood fiber density  $230 \text{ kg/m}^3$  on concrete

Complete dry system for high-displacement thermal roofs with Fibertherm wood fiber insulation panels and high-density Isorel wood fiber panels on concrete structure. Excellent system for thermo-acoustic insulation of roofs.

STRATIGRAPHY		DESCRIPTION	QUANTITY m²	PRICE €/m²	AMOUNT
1	Roof tiles	Roof tiles			
2	Support-Spacer type Aercoppo	An element, weighing 36 g, made of polypropylene copolymer stabilized to U.V.A. rays, with the function of raising and anchoring, to be applied on the back of each tile roof. It creates, a true ventilation chamber of 600 cm $^2$ /m underlay, raising the channel tile only 3.5 cm from the laying surface.			0
3	Anti-steam barrier FiberTherm multi UDB	High airtight sealant vapor barrier for renovation solutions. Extreme ease of installation for safe and simple use. It has an integrated adhesive strip to secure joints and can be used as a temporary cover. Size: $1,50 \text{ m} \times 50 \text{ m}$ Roll surface: $75\text{m}^2$ Weight approx. $160 \text{ g/m}^2$			0
4	Wood fiber panels Fibertherm Isorel 230 thicknesses 19 mm	The panels are made of wood ber with density $\sigma$ =230 Kg/m³, are produced with a wet system, in compliance with EN 13171 and EN 13986 standards under constant quality control. The material is characterized by the following thermodynamic characteristics: thermal conductivity coeff. $\lambda$ =0,05 W/mK, specific heat c=2100 J/kg K, resistance to vapor penetration coeff. $\mu$ =5 and reaction to fire class E, according to EN 13501-1 standard. The panel dimensions are mm for a thickness of mm.			0
5	Wood fiber panels Fibertherm 160 (2 layers) available thicknesses: 60+60 mm 80+80 mm 100+100 mm	The panels are made of wood ber with density $\delta$ =160 Kg/m³, are produced with a wet system, in compliance with EN 13171 and EN 13986 standards under constant quality control. The material is characterized by the following thermodynamic characteristics: coefficient of thermal conductivity $\lambda$ =0.039 W/mK, specific heat c=2100 J/Kg K, coefficient of resistance to vapor penetration $\mu$ =5 and reaction to fire class E, according to EN 13501-1 standard. The dimensions of the panels correspond to mm for a thickness of mm. The wood used in the processing of the panels comes from forests controlled by FSC reforestation cycles.			0
6	Steam brake FiberTherm multi membra 5	Steam brake for better airtightness on the outer side of the roof, resistant to UVrays, excellent adhesion properties and tear resistance.  Size: 1,50 mx50 m Roll surface: 75m² Weight approx.110 g/m²			0
7	Concrete roof	Concrete structure with slats and hollow bricks   thickness 200+40 mm			
		TAX IVA 22%	0	TAXABLE	0
TOTAL AMOUNT					0

Beton Wood®

The functionality of the system will be covered by a BetonWood guarantee for the characteristics of air tightness, water proofing and isolation of the technological package. The warranty will be documented with the appropriate Certificate and Certificate of Assurance that will be delivered at the end of the work to the DD.LL. from the same layer. The forms are available on the BetonWood website as well as the technical indications, the application matrix and the exclusion clauses.